NC/QC/W-06/2018-19/HN-CB10 **Date: 29-04-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).

{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	22-04-19	29-04-19	07	22500	525	23.33	**22.89**
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	505	22.44	

Page No. 1/1,

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NC/QC/W-06/2018-19/HN-CB11 **Date: 29-04-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	22-04-19	29-04-19	07	22500	520	23.11	**22.74**
	002	"	"	"	"	510	22.67	
	003	"	"	"	"	505	22.44	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/W-06/2018-19/HN-CB12 **Date: 30-04-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).

{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	23-04-19	30-04-19	07	22500	535	23.78	**23.41**
	002	"	"	"	"	520	23.11	
	003	"	"	"	"	525	23.33	

Page No. 1/1,

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

NC/QC/W-06/2018-19/HN-CB13

Date: 02-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	24-04-19	02-05-19	08	22500	530	23.56	**22.96**
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	505	22.44	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB14

Date: 02-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	24-04-19	02-05-19	08	22500	525	23.33	**22.81**
	002	"	"	"	"	505	22.44	
	003	"	"	"	"	510	22.67	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer,
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/W-06/2018-19/HN-CB5a **Date: 09-05-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	11-04-19	09-05-19	28	22500	730	32.44	**32.81**
	002	"	"	"	"	750	33.33	
	003	"	"	"	"	735	32.67	

KIRAN. R
M.E, (Civil Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB6a

Date: 11-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-04-19	11-05-19	28	22500	735	32.67	**33.11**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	755	33.56	

K.R
KIRAN. R
M.E, (Civil-Engg)

Page No. 1/1,

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NC/QC/W-06/2018-19/HN-CB7a

Date: 11-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-04-19	11-05-19	28	22500	765	34.00	**33.48**
	002	"	"	"	"	740	32.89	
	003	"	"	"	"	755	33.56	

KIRAN. R
M.E, (Civil-Engg)

Page No. 1/1,

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone

Proprietor

NC/QC/W-06/2018-19/HN-CB8a

Date: 14-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-04-19	14-05-19	28	22500	760	33.78	**33.56**
	002	"	"	"	"	750	33.33	
	003	"	"	"	"	755	33.56	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.

NC/QC/W-06/2018-19/HN-CB9a **Date: 16-05-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-04-19	16-05-19	28	22500	755	33.56	**33.11**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	735	32.67	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB10a **Date: 20-05-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	22-04-19	20-05-19	29	22500	745	33.11	**33.56**
	002	"	"	"	"	755	33.56	
	003	"	"	"	"	765	34.00	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Proprietor

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB11a

Date: 20-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1.	001	22-04-19	20-05-19	28	22500	735	32.67	**32.67**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	725	32.22	

K.R
KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB12a **Date: 21-05-2019**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	23-04-19	21-05-19	28	22500	735	32.67	**33.04**
	002	"	"	"	"	755	33.56	
	003	"	"	"	"	740	32.89	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,16TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/W-06/2018-19/HN-CB13a

Date: 22-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}
Ref.: Material testing/PMC/18-19,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.
Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	24-04-19	22-05-19	28	22500	760	33.78	**33.41**
	002	"	"	"	"	750	33.33	
	003	"	"	"	"	745	33.11	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer
Project Division
Yelahanka Zone

Proprietor

NEWZEN CONSULTANT BANGALORE, #1316 1ST MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056 CONTACT NO: +91 8792620221, 080 23241187

NC/QC/W-06/2018-19/HN-CB14a

Date: 22-05-2019

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Improvements to Roads, Drains and Culverts at Varadarajaswamy Layout, Varadaraj anagara, Muniswamappa, Ramachandrapura, Kuvempunagara, Singapura Village, Gangammanagudi Surrounding Balaji Layout, Raghavendra Colony and Teachers Layout in Ward No.11.}

Ref.: Material testing/PMC/18-19,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. Gopi Reddy.K, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	24-04-19	22-05-19	28	22500	765	34.00	**33.26**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	735	32.67	

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore

Asst. Executive Engineer,
Project Division,
Yelahanka Zone
Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com